



Plugging and abandoning well strategies for storage development

Sarah Gasda

Research Director, NORCE Energy


Professor II, Dept. Physics & Technology, University of Bergen

11. FEBRUAR 2020


Millions of wells worldwide (as of 2005)


- High density in regions of mature regions
- Designed for petroleum production and lifetime of max 50 years
- Many are still active
- All will be eventually abandoned
- IPCC 2005 data, already <u>outdated</u> because thousands of wells are drilled and abandoned each year!

Global well infrastructure, 2005





IPCC, 2005 – Bert Metz, Ogunlade Davidson, Heleen de Coninck, Manuela Loos and Leo Meyer (Eds.) Cambridge University Press, UK.






Norwegian Petroleum Directorate (2020) https://www.npd.no/fakta/bronner/





Wellbore Integrity

- All wells are eventually plugged and abandoned
- Integrity is dependent as much on initial well completion as abandonment procedure
 - Neither is always perfect
- Plug can be cement or bridge
 - Type and quality of the plug is important
- Initial state is important before added impact of chemical attack or mechanical fatigue



Plugging & Abandonment in Canada







Fig. 1—Typical well abandonments in Alberta, Canada: (a) drilled and abandoned open hole; (b) cased, completed, and abandoned.

Legacy well leakage

- Field evidence that legacy wells can leak.
- Well documented cases in N. America
 - Surface casing vent flow (SCVF) in Alberta; monitoring required by regulations (*Watson and Bachu, SPE 106817*)
 - Sustained casing pressure (SC) in US (*Lackey et al. ES&T 2017*)
- Measurement campaigns have documented methane leaks from old wells in Pennsylvania
 - 100 yr-old oil wells in USA in western PA
 - Kang et al., Proc. Natl. Acad. Sci. 2014



Watson and Bachu, SPE 106817, 2009





Kang et al., Proc. Natl. Acad. Sci. 2014

Legacy well leakage

- Data are important for evaluating potential for leakage in CO₂ storage
- Type of abandonment (regulations) has a high impact on leakage
- Cased holes are more likely to leak
- Leakage is from shallower zones than the original completion depth.


Minority of wells are problematic Only 5% of well infrastructure have recorded leaks in Alberta






Watson and Bachu, SPE 106817, 2009

Central North Sea measurements





L. Vielstädte et al./Marine and Petroleum Geology 68 (2015)



Measurement campaign at 3 wells in 2015 First public study to quantify methane leaks Max rate 0.15 L/min Geochemical, bubble sampling, video

Central North Sea measurements






Wells in vicinity of Sleipner, but not related Source zone is shallow depth Gas origin is biogenic Leakage rate is comparable to natural seeps

From natural seeps to CO₂ storage



Leakage is interesting, but tells only part of the story

- Well properties (and not the leakage itself) are needed to predict impact on CO₂ storage
- Efforts to estimate hydraulic properties
 - Direct testing of legacy wells by down-hole intervention (VIT)
 - Indirect estimation from leakage rates at surface
- Both methods give estimates that can be used to further to constrain potential for leakage for CO₂ storage development



Field Survey

Evaluate barrier system

Mechanical integrity (caliper)


Cement bond log/ultrasonic scanner tools


Vertical Interference Test

Detect signs alteration by CO_2 migration.


Fluid/gas samples

Sidewall cores through the casing





Crow et al., Wellbore integrity of a CO₂ producer, *IJGGC*, (2010)



16000


Crow et al., Wellbore integrity of a CO₂ producer, *IJGGC*, (2010)


Integrity test results

- No visual signs of cement degradation from sidewall cores.
- CO₂ has altered cement barrier system along the caprock to varying degrees.
 - Higher amounts of calcium carbonate near CO₂ reservoir.
 - Carbonation effect is evident in fluid/gas analyses.










Integrity test results


Permeability measurements indicate that interfaces are primary flow pathway.

Lab analysis of cement perm are in the microD range.

Lowest VIT estimate of effective perm is 0.1 milliD.



Crow et al., Wellbore integrity of a CO2 producer, *IJGGC, (2010)*



Field test summary: Effective permeability vs cement permeability

Reported VIT data	Estimated Wellbore permeability	Measured Cement permeability
ССР	1.7 mD	0.1 – 32 microD
TPX	170 mD	0.1 – 449 microD
CC1	25 mD	0.001 – 4.63 mD
Hypothetical VIT data		
CCP upper bound	100 D	
CCP lower bound	0.01 mD	
Unreported VIT data		
3 datasets	6 mD – 3 D	1.3993
		• •

N R C E

Source: Gasda, et al., Energy Procedia 37 (2013); Crow et al., IJGGC, (2010); Duguid et al., Greenhouse Gases: Science and Technology (2017)


Surface leakage measurements and wellbore permeability estimates


- Direct measurements of leaked volumes in time can be used to estimate permeability
- Uncertainty of source depth and other parameters
- No wells greater than 1 Darcy permeability

Location	Number of wells	Wellbore permeability
British Columbia ¹	736	$10~\mu D - 10~mD$
Pennsylvania ²	42	1 nD 100 mD
Central North Sea**	1	100 mD – 1 D

- Cubic law for annular aperture
 - 5 µm (1mD) to 0.2 mm (100 Darcy)


¹Tao, Q.; Bryant, S. L. Well permeability estimation and CO2 leakage rates. Int. J. Greenhouse Gas Control 2014, 22, 77–87 **approximation by S. Gasda






From parameters to prediction

- Simulation technology can be used to understand the potential for leakage in prospective CO₂ storage regions
- Advances in modeling gives very accurate simulation of wellbore flow over many wells in real geological system with multiple strata
- "Elevator effect" with CO2 flow into thief zones dampens eventual leakage to surface




Class et al., Comp Geosci, 2009




Case study: Well leakage in Alberta


1146 total wells in 30 x 30 km area









Nogues et al., A methodology to estimate maximum probable leakage along old wells in a geological sequestration operation, IJGGC 2012











a ₁₀₀ Percent (%) leaked after 50 yrs 9 are intact 80 that 70 2 Percent (%) of well sections 60 0.01 10 0 -10 -12 -13 -14 -11 -15 Mean log, K of Degraded Well

Percent (%) leaked after 50 yrs а 100 -0.10 0.000 90 Percent (%) of all wells that are intact 80 70 60 0.001 0005 .0.01 0.00 50 0 40 30 20 .000 -10 -12 -15 -11 -13 -14 Mean log, K of Degraded Well Leakage into top two aquifers (<750 m)










Most leakage is within acceptable bounds for climate change

Measured wells < 1 Darcy produces < 0.1% leakage after 50 years


Very difficult to produce significant leakage through degraded wells



Future of P&A offshore



- Preparing for a wave of plug and abandonment as many platforms are heading towards decommissioning
- "Restoring the caprock" (rock-to-rock)
- Bring down costs (rigless plugging)
- Improve plug integrity, examine bridge plugs and plug length
- Section milling
- Shale barriers
- Cut-and-pull operation



Fluid migration modelling & treatment KPN project in PETROMAKS2 program 2019

- 10-m portions of a 30-yr Valhalla well recovered for testing of barrier quality
- Cemented sandwich sections, generally good cement bond that agrees with logs and low gas migration by direct physical testing
- Liquid permeabilities in microDarcies. Gas permeability in milliDarcies
- Unique opportunity to develop new treatment technologies
- Improved understanding of migration paths can guide the choice of remedial action to establish well integrity, improve SCP management and support the selection of the right P&A design solution
- Project objectives:
 - Realistic micro-annuli and crack geometries
 - Fluid migration analysis and **placement of treatment materials**
 - **Full-scale test assemblies** for qualification of treatment technologies







The future for P&A and CO₂ storage



Wells will most likely leak, many wells already do.

Leakage from legacy wells may not be problematic from a climate or environmental perspective

Monitoring requirements will require assurance that all leakage is detected

Need for clear regulations for P&A requirements within context of large-scale CO2 storage deployment

The future for P&A and CO₂ storage



• Discussion points

- How to ensure Plug and Abandonment is good enough for long-term CO₂ storage?
- Should all leaks be stopped? Or even can a leak be stopped?
- Is it good enough to monitor for crediting or offsetting the leaked CO₂ another way?
- Can we build confidence by demonstrating successful remediation on leaky wells (biogenic gas)?



Thank you for your attention!

SARAH GASDA

- sarah.gasda@norce.research.no
- https://www.norceresearch.no/en/research-theme/ccus

References



S.E. Gasda, S. Bachu and M.A. Celia (2004) Spatial characterization of the location of potentially leaky wells penetrating a deep saline aquifer in a mature sedimentary basin. Environmental Geology, 46(6-7), 707-720. doi:10.1007/s00254-004-1073-5

Watson and Bachu (2009) Evaluation of the Potential for Gas and CO2 Leakage Along Wellbores, SPE 106817 SPE Drilling & Completion.

M. Kang, et. al. (2014) Direct measurements of methane emissions from abandoned oil and gas wells in Pennsylvania. Proceedings of the National Academy of Sciences, 111 (51) 18173-18177; DOI:10.1073/pnas.1408315111

L. Vielstädte, et al. (2015) Quantification of methane emissions at abandoned gas wells in the Central North Sea, Marine and Petroleum Geology, 68, Part B, 848-860, <u>https://doi.org/10.1016/j.marpetgeo.2015.07.030</u>.

W. Crow, J.W. Carey, S.E. Gasda, D.B. Williams and M.A. Celia (2010) **Wellbore integrity of a CO2 producer**. International Journal of Greenhouse Gas Control, 4 (2), 186–197. doi:10.1016/j.ijggc.2009.10.010

S.E. Gasda, J.Z. Wang and M.A. Celia (2011) Analysis of in-situ wellbore integrity data for existing wells with long-term exposure to CO2. Energy Procedia, Proceedings GHGT- 10, 4, 5406–5413. doi:10.1016/j.egypro.2011.02.525

Tao, Q.; Bryant, S. L. (2014) Well permeability estimation and CO2 leakage rates. Int. J. Greenhouse Gas Control, 22, 77–87, https://doi.org/10.1016/j.ijggc.2013.12.022

M. Kang, et al. (2015) Effective Permeabilities of Abandoned Oil and Gas Wells: Analysis of Data from Pennsylvania, Environ. Sci. Technol., 49, 4757–4764, DOI: 10.1021/acs.est.5b00132

H. Class, et al. (2009) A benchmark-study on problems related to CO2 storage in geologic formations: Summary and discussion of results. Computational Geosciences, 13(4), 409–434. doi:10.1007/s10596-009-9146-x

Nogues et al. (2012) A methodology to estimate maximum probable leakage along old wells in a geological sequestration operation, IJGGC, 7, 39–7, doi:10.1016/j.ijggc.2011.12.003

T. Vrålstad, et. Al. (2019) Plug & abandonment of offshore wells: Ensuring long-term well integrity and cost-efficiency, Journal of Petroleum Science and Engineering, 173, 478-491, https://doi.org/10.1016/j.petrol.2018.10.049.

Skadsem et al. (2020) Fluid Migration Characterization of Cemented Sections retrieved from a North Sea Production Well, SPE-199662-MS

Guillermo et al. (2020) An Evaluation of the Cement Sheath Quality of Casing Sections Recovered During a Well Abandonment Operation, SPE-199609-MS